



SOLID T&G PLANK FLOORING - SECRET NAILED INSTALLATION GUIDELINES

The following should be used for guideline purposes only, as it is the responsibility of the installation contractor to ensure that floors are installed correctly and safely, subject to the relative site conditions, sub floor and specified finish.

These guidelines are designed to complement the current British Standard BS8201 and any other relevant standards of manufacturer's instruction.

SITE CONDITIONS

Before materials are delivered to site, all wet trades should be complete and dried out. The building must be weather tight, i.e. doors and windows fully fitted.

Site conditions should be checked to ensure the humidity levels are - and are maintained at - between 45% and 65% RH, and the room temperature between 15°C and 25°C.

Extremes of temperature / humidity will affect the stability of wood flooring. Low humidity can cause the wood to shrink, and a high level to cause expansion. Typical causes of low humidity are the use of heating at too high a temperature, open fires and wood burners.

We recommend using a thermometer / hygrometer to monitor temperature and humidity. A humidifier / de-humidifier can be used to control the ambient conditions.

As a general guide, areas should be adequately ventilated to prevent a build-up of moisture in the atmosphere. Wood will naturally change its size during the progress of the seasons. In the summer, the humidity is generally at its highest level and wood joints should be reasonably tight together.

During the winter, when heating is typically used, the humidity levels are generally lower and wood flooring will naturally show small gaps between the joints.

This is natural movement and not a manufacturing or installation fault.

The wood flooring should acclimatize in the room where the wood is to be fitted for at least 72 hours prior to installation to balance with the environment it is going to be used in. It should be stored out of direct sunlight, away from walls and radiators and on battens fully supporting the wood to prevent a build of heat on the bottom boards.

UNDER FLOOR HEATING

Solid T&G wood flooring cannot be installed over under floor heating.

SUBFLOOR REQUIREMENTS

The subfloor must be sound, clean, dry and flat to British Standard SR1 tolerance: a maximum 3mm gap under a 2m long straight edge at any point across the sub floor.

◆ TIMBER SUBFLOOR

Timber subfloors must be sound and level. It should be tested using a Protimeter or similar moisture meter. The moisture content of the timber subfloor must be less than 14% WME.

All suspended wood floors must have suitable through ventilation, usually delivered by air bricks in the outside walls. Any wood subfloor that has a moisture level in excess of 14% should be investigated. It must also be free of infestation such as wood-rotting fungi and boring insects. We would recommend installing a plywood of minimum 6mm thickness, complying with BS EN 314-1:2004 Class 3 (formerly referred to as WBP) over all timber subfloors, laid at 90° to the run of existing floorboards.

INSTALLATION

As a general rule of thumb, subject to site conditions and overall width span of area, an expansion gap of 1.5mm per linear metre run throughout the expanse of the flooring is required to the perimeter of the floor, with a minimum expansion gap of 10mm. Dependant on the size of the floor area to be laid some provision may also be required within the body of the floor. This is to allow for changes in ambient conditions, especially changes in humidity, which can cause wood floors to move appreciably. Unless suitable provision is made to accommodate movement, the stability of surrounding walls can be affected or undesirable changes in the floor surface might result.

Expansion gaps should also be provided at all other abutments such as radiator pipes, thresholds, door linings, floor sockets, etc.

Expansion gaps can be covered using scotia / quadrant / flat bead / skirting. For areas where these products cannot be used, for example in front of a stone fireplace, an alternative such as a cork expansion strip or mastic joint can be used.

Threshold profiles should be installed in all doorways, arches or



narrow sections that lead from one room / area to another. These thresholds must allow for the required expansion and contraction. Door frames and architraves can be undercut to allow the wood to slide underneath, still allowing for expansion.

Our recommendation for larger areas would be to fully glue to product with a flexible adhesive.

For further information on expansion gaps see the [BSI website](#); BS 8201:2011.

Newel posts should never be undercut, as these are structural sections of the stairs.

The flooring should be taken from three separate packages and not all from one pack, to avoid areas being installed from the same batch of wood.

Any boards over 140mm wide should be glued and secret nailed. Boards less than 140mm wide can be secret nailed only.

Boards 140mm or under can be secret nailed over joists, with a bitumen paper or similar lapped over the joists by at least 100mm – prior to the boards being laid – to prevent ingress of moisture from the void underneath. If a board wider than 140mm is required, we recommend installing an 18mm plywood subfloor over the joists, then gluing and nailing the boards to this plywood.

Secret nailing should be completed using a pneumatic nailer with barbed nails, i.e. Powernailer or Portanailer. The length of the nails should be suitable for the thickness of the board and the subfloor they are going into. If fixed to plywood, boards should be nailed at approximately 300mm – 400mm centres and at 100mm from either end of each board. If fixed to joists, boards should be nailed on every joist and PVA should be used on all header joints.

If appropriate, the wood flooring should be fully bonded to the prepared sub floor using a suitable flexible adhesive. This should be applied using a notched trowel, following adhesive manufacturer's instructions, including for notch size.

When planning the layout of the area, you may wish to balance the board width against the two most prominent walls, taking into account focal points such as fireplaces. This is more critical in smaller areas than in larger areas, where you cannot visualize both sides at the same time. Aim to have at least half a board width at each side, as smaller width boards are difficult to fit and highlight any discrepancies in the straightness of the walls.

The selection of a layout is, of course, an aesthetic matter.

If boards are over 140mm and being glued as well as nailed, we would recommend dry-laying the first two or three rows, adjusting the first row to the wall contours and adjusting for the width you have planned. Ensure there is at least 300mm between the header joints, and ideally 500mm – or at least two times the width of the board. Once done, mark a glue line on the sub floor and move the boards whilst applying the adhesive. Immediately place the boards into the adhesive which must be prior to the adhesive skinning over. Place spacers between the boards and the wall to maintain the expansion gap whilst the adhesive is curing.

Nailing should be completed whilst glue is still wet.

If the installation continues over more than one day, strap or wedge the last row to prevent movement overnight. Weight down the last few rows to prevent them lifting off from the adhesive. If the boards do not close easily, you may need to use a knocking block or lever bar to assist in this placement.

SANDING & TREATMENT (UNFINISHED PRODUCTS)

Once installed the flooring should be left to acclimatize for a further 10 x days, prior to sanding and finishing.

The flooring should be sanded flat progressively through sandpaper grits, filled with a resin mixed with fine sawdust and then fine sanded and finished with a trio or similar machine.

Aged & Distressed products should be lightly buffed (not fully sanded or filled) to prepare the surface for finishing.

The chosen stain, oil or lacquer product should then be applied in accordance with the manufacturer's recommendations.

ONGOING CONDITIONS

The most critical time for newly installed wood flooring is during and for 48 hours after the installation. Allowing the temperature or humidity to alter, particularly overnight when temperature can drop can cause the wood to lift slightly away from adhesive, affecting the bond.

Throughout the life of the floor, we recommend that the temperature should be maintained between 15°C and 25°C, and relative humidity levels between 45% and 65%, which will keep any movement within the floor to a minimum and ensure that the floor remains stable. As with any wooden floor, if humidity levels rise or fall outside of these parameters, a greater degree of shrinkage or expansion would be expected to occur. ■